

ACRYLIC FACADE PAINT

KLEIB PROFESSIONAL Q1 is part of a product set used for the KLEIB building insulation system in compliance with Technical Approval no. AT-15-8239/2013 issued by the Building Research Institute in Warsaw.

USE

KLEIB PROFESSIONAL Q1 is an acrylic facade paint used primarily for painting thin-layer mineral or acrylic plasters in the KLEIB building insulation system.

SUBSTRATE PREPARATION

The substrate should be dry, stable and solid (i.e. appropriately strong and purified of any layers that could weaken the paint's adhesion). New mineral plasters can be painted no sooner than after 4÷6 weeks, whereas acrylic plasters at least after one week.

PAINT PREPARATION

KLEIB Q1 paint is provided ready-for-use. After opening the bucket, the contents should be mixed in order to smoothen the product's consistency.

APPLICATION

Apply thin, even coats of paint by using a brush or a roller or by spraying it. Depending on the structure and absorbency of the substrate, multiple coats of paint may be applied. Each subsequent layer should be applied after the previous one has dried, but no sooner than after 4 hours.

PRODUCT CONSUMPTION

Average when applying a single coat on an even surface: 0.10 - 0.20 l/m².

STORAGE AND TRANSPORTATION

KKLEIB PROFESSIONAL Q1 must be stored in airtight buckets in dry conditions and above zero temperatures for a maximum of 12 months after the production date found on the label.

TECHNICAL SPECIFICATION

Bulk density		1.57 g/cm ³ ± 10%
Percentage of dry substance		68.3 -3.1/+6.8
Percentage of ash	in 450°C	76.6 ÷ 80.6
	in 900°C	49.9 ÷ 53.9
Surface and ambient temperature during application		Between +5°C and +25°C
Drying time		2 - 4 hrs.

This product is compliant with Technical Approval no. AT-15-8239/2013.

National Declaration of Conformity no. ... for the KLEIB insulation system.

This product comes with a Hygienic Approval.

Certifying authority that participated in the evaluation of conformity: Building Research Institute Filtrowa 1,
00-611 Warsaw.

Construction mark B.

MANUFACTURER

KLEIB Sp. z o.o.

Kolejowa 15 - 17

87-880 Brześć Kujawski

Phone/Fax: 54 233 82 83

PRODUCED IN THE FOLLOWING PLANT:

KLEIB Sp. z o.o.

Kolejowa 15 - 17

87-880 Brześć Kujawski

Production date: