



# ADHESIVE MORTAR



- high yield
- easily workable
- · increased adhesion and very high degree of flexibility
- for white and graphite polystyrene

KLEIB C1 is an element of the external thermal insulation composite system with rendering (ETICS) marketed under the trade name KLEIB.



Thermal insulation system based on polystyrene

#### **USE**

KLEIB C1 is an adhesive cement mortar designed to attach polystyrene sheets to a substrate in the KLEIB system. It is also suitable for fixing polystyrene sheets on all typical, structurally sound and even mineral substrates (concretes, renders, brickwork, hollow blockwork, stone elements, cement boards) and insulated concrete formwork.

### **WORKING SURFACE PREPARATION**

The working surface should be stable, even and structurally sound i.e. strong enough, and free from any layers that might weaken the mortar's adhesion, in particular dust, dirt, lime, oil, grease, wax, or remains of emulsion and oil paint. If the surface is too absorbent, it should be cleaned and primed. For this works it is best to apply KLEIB G1 primer.

### **MIXING THE MORTAR**

The mortar is prepared by pouring the entire contents of the bag into a container with a measured amount of water and mixing until a smooth, lump-free uniform consistency is obtained. The mortar is ready to use after 5 minutes and after remixing. Prepare portions that are to be used within approx. 2 hours.

#### INSTRUCTIONS FOR USE

For bonding polystyrene sheets on even surface, it is advisable to apply the mortar on the entire surface of the insulation sheets and spread it with a notched plasterer's float. Before bonding graphite polystyrene, it should be sanded to enhance the grip of the adhesive mortar. In case of an uneven working surface, the mortar should be applied to the sheet in the form of thick layers along its edges, at the distance of approx. 5 cm from the edge, along with 3 to 6 patches of mortar uniformly distributed on the rest of the sheet's surface. As a result a min. 60% of the surface must be sufficiently adhered to the working surface. Vertical connection of the sheets should be maintained in a staggered arrangement. Further work, i.e. any use of suitable fasteners, grinding of uneven surfaces of sheets, or the application of a reinforced layer can be performed no earlier than after 72 hours. The use of protective nets on scaffolding is recommended. Tools should be washed with water immediately after use.

## **USAGE**

Approximately 4.0-5.0 kg/m<sup>2</sup>.

## STORAGE AND TRANSPORT

The mortar must be transported and stored in tightly sealed bags, in dry conditions. Protect from dampness. Shelf life in conditions that comply with the specified requirements is 12 months from the production date on the packaging.

## **TECHNICAL SPECIFICATIONS**

Mixing ratio	0.18-0.20 litres of water per 1 kg of mortar
	4.50-5.00 litres of water per 25 kg of mortar
Working surface temperature and ambient temperature during work	between +5°C and +25°C









# EAD 040083-00-404 ETA 16/0978

KLEIB sp. z o.o. Pikutkowo 43, 87-880 Brześć Kujawski

> tel.: +48 54 233 82 83 www.kleib.pl

Unique identification code of the product type: KLEIB ETICS

Reference number of the declaration of performance: 1 KLEIB/2017



The ETICS system is designed to be used as an external thermal insulation of walls of new buildings, and for renovation of the existing ones.

UFI: K110-1068-7002-STQR

## **DANGER**

Contains Portland cement, Portland cement dust.

H315 Causes skin irritation.

H317 May cause an allergic skin reaction.
H318 Causes serious eye damage.
H335 May cause respiratory irritation.

P261 Avoid breathing dust.
 P280 Wear protective gloves/protective clothing/eye protection/face protection.
 P305 IF IN EYES: Rinse cautiously with water for several minutes.
 P351 Remove contact lenses, if present and easy to do. Continue rinsing.

P338
P302 IF ON SKIN: Wash with plenty of soap and water.

P310 Immediately call a POISON CENTER or a doctor/physician.
P501 Dispose of contents/container to properly labelled waste containers in accordance with national regulations.

The content of soluble chromium (VI) in the product is below 2 ppm throughout the shelf life provided on the packaging. After that time, the risk of a chromium allergy increases.



